

PAT-NO: JP363145362A
DOCUMENT-IDENTIFIER: JP 63145362 A
TITLE: PRODUCTION OF HYDROPHILIC POLYURETHANE FOAM
PUBN-DATE: June 17, 1988

INVENTOR-INFORMATION:

NAME
KAWAKAMI, HIROSHI

ASSIGNEE-INFORMATION:

NAME	COUNTRY
ACHILLES CORP	N/A

APPL-NO: JP61292165

APPL-DATE: December 8, 1986

INT-CL (IPC): C08L075/04, C08G018/48

US-CL-CURRENT: 521/88

ABSTRACT:

PURPOSE: To obtain the title foam which has excellent water absorbing proper ties, water permeability and tensile strength after water absorption and is suit able for use in the fields of hydroponic culture, toy, etc., by blending a specified polyol with a polyisocyanate, a blowing agent, a foam stabilizer, a trioxyethylenedimethylamine catalyst and epoxidized soybean oil and heating the mixture.

CONSTITUTION: 100pts.wt. polyol (A) having an average MW of 1,500~7,000, a weight ratio of ethylene oxide to propylene oxide of 10/90~70/30 and an average number of functional groups of 2~3.5 is blended with 0.01~5.0pts.wt. trioxyethylenedimethylamine (B) as

a
catalyst, 0.01~2wt.% (based on the amount of component B)
epoxidized
soybean oil (C) as an additive, a blowing agent (D) (e.g.,
trichloromonofluoromethane) and a foam stabilizer (E) (e.g., silicone
foam
stabilizer). A polyisocyanate (F) (e.g., tolylene diisocyanate) is
added there
to and the mixture is expanded.

COPYRIGHT: (C)1988, JPO&Japio